PATENT ABSTRACTS OF JAPAN

(11)Publication number:

10-106441

(43)Date of publication of application: 24.04.1998

(51)Int.Cl.

H01J 11/00

H01J 11/02

(21)Application number : 08-261639

(71)Applicant: FUJITSU LTD

(22)Date of filing:


02.10.1996

(72)Inventor: HIDAKA SOICHIRO

IWASE NOBUHIRO TADAKI SHINJI

MOCHIZUKI AKIHIRO

(54) PLASMA DISPLAY PANEL



(57)Abstract:

PROBLEM TO BE SOLVED: To enhance sputtering resistance of a protective film by arranging a magnesium oxide film of a 110 orientation.

SOLUTION: An MgO film of a 110 orientation is formed as a protective film on a surface of a dielectric layer of PbO type low melting point glass of a plasma display panel. A glass substrate on which a sustained electrode and the dielectric layer are formed is fixed in an evaporation device chamber, and as one example, oxygen partial pressure is kept in 1 × 10-4Torr, and steam partial pressure is kept in a constant value, and evaporation is

performed. Hydrogen gas and oxygen gas are introduced, and for example, the steam partial pressure is set in a range not more than 5×10 –4Torr, and the 110 orientation

is enhanced according to an increase in the steam partial pressure exceeding 1×10 –4Torr. When the membrane of the MgO film formed into the dielectric layer is taken as 110 orientation, a membrane close to high density bulk is obtained, and sputtering resistance can be enhanced.

CLAIMS

[Claim(s)]

[Claim 1]A plasma display panel characterized by coming to provide a magnesium oxide film of orientation (110) as a surface-protection film of a dielectric layer which covers a display electrode.

DESCRIPTION OF DRAWINGS

[Brief Description of the Drawings]

[Drawing 1]It is an exploded perspective view showing the internal structure of PDP concerning this invention.

[Drawing 2]It is a figure showing orientation distribution of a protective film.

[Drawing 3]It is a graph which shows the relation between a steam partial pressure and the crystal orientation of a MgO film.

[Description of Notations]

- 1 PDP (plasma display panel)
- 17 Dielectric layer
- 18 Protective film (surface-protection film)
- X, Y sustaining electrode (display electrode)